

## Hygrothermal viscoelastic material characterisation of unidirectional continuous carbon-fibre reinforced polyamide 6

van Dijk, Y. L.M.; Grätzl, T.; Abouhamzeh, M.; Kroll, L.; Shroff, S.

**DOI**

[10.1016/j.compositesb.2018.05.054](https://doi.org/10.1016/j.compositesb.2018.05.054)

**Publication date**

2018

**Document Version**

Accepted author manuscript

**Published in**

Composites Part B: Engineering

**Citation (APA)**

van Dijk, Y. L. M., Grätzl, T., Abouhamzeh, M., Kroll, L., & Shroff, S. (2018). Hygrothermal viscoelastic material characterisation of unidirectional continuous carbon-fibre reinforced polyamide 6. *Composites Part B: Engineering*, 150, 157-164. <https://doi.org/10.1016/j.compositesb.2018.05.054>

**Important note**

To cite this publication, please use the final published version (if applicable). Please check the document version above.

**Copyright**

Other than for strictly personal use, it is not permitted to download, forward or distribute the text or part of it, without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license such as Creative Commons.

**Takedown policy**

Please contact us and provide details if you believe this document breaches copyrights. We will remove access to the work immediately and investigate your claim.

# Hygrothermal viscoelastic material characterisation of unidirectional continuous carbon-fibre reinforced polyamide 6

Y. van Dijk<sup>a,\*</sup>, T. Grätzl<sup>b</sup>, M. Abouhamzeh<sup>a</sup>, L. Kroll<sup>c</sup>, S. Shroff<sup>a</sup>

<sup>a</sup>*Faculty of Aerospace Engineering, Delft University of Technology, Kluyverweg 1, 2629 HS Delft, The Netherlands*

<sup>b</sup>*Department of Technology Development of Fibre-Reinforced Plastics, BMW Group, Ohmstraße 2, D-84030 Landshut, Germany*

<sup>c</sup>*Department of Lightweight Structures and Polymer Technology, Technische Universität Chemnitz, Reichenhainer Straße 31/33, D-09126 Chemnitz, Germany*

---

## Abstract

This paper presents results of material characterisation experiments on the hygrothermal viscoelastic behaviour of unidirectional laminates of continuous carbon-fibre reinforced polyamide 6. The material behaviour when subjected to the automotive painting process is of interest. Coefficients of thermal- and -moisture expansion were determined from dilatometer experiments and micrometer measurements together with weighing, respectively. Diffusion coefficients were generated from thermogravimetric analysis and fitted with the Arrhenius equation. Dynamic mechanical analysis and digital image correlation of quasi-static tensile tests were performed to obtain a relaxation curve and a major Poisson's ratio, respectively. The Williams-Landel-Ferry equation was fitted to the time shift factors.

*Keywords:* A. Carbon fibre, A. Thermoplastic resin, B. Thermomechanical, B. Rheological properties, X. Hygroscopy

---

## 1. Introduction

The application of composite materials in the body structure of passenger vehicles has seen a gradual increase over the past few years due to the efforts made in the automotive industry to restrain the trend of increasing kerb weight [1, 2, 3]. Structural composite parts in the automotive industry most often feature a thermoset matrix due to lower raw materials costs in  
5 comparison to a thermoplastic equivalent [4]. However, legislative changes to the requirements

---

\*Corresponding author

*Present address:* Oranje Nassaplein 17, 3708 BL, Zeist, The Netherlands (Y. van Dijk)

*Email address:* [yannickvdijk@gmail.com](mailto:yannickvdijk@gmail.com) (Y. van Dijk)

on recyclability of newly produced vehicles have led to the interest in utilising polymers with a thermoplastic nature because of the possibility to recycle [5]. Contrarily, composites made of thermoset matrix material cannot be remelted because of cross-linking [6, 7]. The matrix-  
10 and fibre material of a continuous fibre-reinforced thermoplastic can be separated by means of melting since a melting temperature exists for thermoplastics. Nevertheless, recyclable composites are often still landfilled due to the difficulties in physically recovering them due to strong connections to other parts [8].

In addition to providing recyclability advantages, thermoplastic composites benefit from  
15 rapid processing, improved fracture toughness and joining possibilities through welding [9, 10, 11, 12, 13]. It must be kept in mind that adapting the conventional automotive process chain of existing vehicle models to optimise the manufacturing process for thermoplastic matrix materials is not sensible from an economical perspective. It must therefore be noted that composite parts are connected to the body-in-white (BIW) in the body shop, which  
20 occurs prior to entering the paint shop. The consequence is that structural parts with a thermoplastic matrix, intended for existing vehicle models, are subjected to the automotive paint shop. The BIW is passed through a series of drying ovens during the automotive paint shop in which a maximum temperature up to approximately 190 °C is encountered [14, 15]. This temperature surpasses the glass transition temperature of economically sensible  
25 thermoplastic matrix materials and the deformation behaviour must be investigated to be able to safeguard the intended geometry and functioning of these structural parts.

The deformation of polymer composites is governed by thermal- and hygroscopic expansion in combination with clamped boundary conditions [16, 17]. The automotive painting process is of special interest due to the deformation that is caused by the imposed thermal loads.  
30 The material characterisation techniques in this study were carried out with polyamide 6 (PA6) as matrix material and were aimed at identifying all necessary material parameters to accurately model the deformation behaviour of thermoplastic composite structural parts during the automotive painting process. It is noted that PA6 is a hydrophilic polymer and absorbs moisture by diffusion [18, 19, 20]. Hence, composite structural parts with PA6 as  
35 matrix material display an increase in moisture concentration as a result of the pre-treatment and cathodic dip painting process. It follows that these parts enter the dryers with a non-zero

moisture content. The moisture diffusion of various polyamides is often conform to Fickian behaviour and can be modelled accordingly [21, 22, 23].

Additionally, thermoplastic materials show some polymer-specific phenomena. Recrystallisation  
40 occurs during the application of the thermal load and results in a higher degree of crystallinity that increases the density of the polymer and yields post-shrinkage [24, 25, 26]. Specifically to PA6, the application of a thermal load also causes a transition of the polymer crystals with a  $\gamma$ -form to an  $\alpha$ -form, leading to an increase in density as well [27, 28]. The effects of recrystallisation and change in crystal form can be modelled by utilising temperature-dependent  
45 coefficients of thermal expansion (CTE), analogous to the approach taken by Heinle and Drummer [29]. Baran et al. also report the importance of including shrinkage due to crystallisation in the modelling of composite manufacturing processes [30]. The determination of a CTE is often carried out by means of a dilatometer, as demonstrated by Gabrion et al. [31]. Characterising the viscoelastic properties of a thermoplastic composite is often performed  
50 through dynamic mechanical analysis (DMA) [31, 32, 33, 34, 35, 36]. Ma et al. proposed a method to measure hygroscopic expansion by means of DMA [37]. Mechanical models to describe the long-term stress relaxation behaviour of structural members are presented by Ascione et al. [38] and Berardi and Mancusi [39, 40]. The long-term creep behaviour of glass-fibre-reinforced polymers (GFRP) was studied by Berardi et al. [41] and successfully  
55 modelled by means of Burger's model. It was concluded that long-term creep effects are relevant in GFRP laminates manufactured with an epoxy matrix. Long-term stress relaxation behaviour of thermorheologically simple materials can also be described by experimental data obtained during short-term testing through the time-temperature superposition principle [42].

This paper presents the results of several material characterisation methods that have  
60 been carried out with specimens taken from unidirectional (UD) laminates of continuous carbon-fibre reinforced PA6. The objective of the study is to identify the hygrothermal- and mechanical response of these laminates. This information will be used later as input for a numerical model to simulate the deformation behaviour of multi-directional laminates, manufactured with identical material, subjected to the automotive painting process.

## 65 2. Material and methods

Various experiments have been carried out to identify the hygrothermal viscoelastic material behaviour of the UD carbon-fibre reinforced PA6 for which the details are provided (See Section 2.1). All investigated specimens were conditioned to either a fully dry state or to a saturated moisture content, depending on the requirement as per material characterisation  
70 technique. The conditioning was carried out according to the procedure that is described in DIN EN ISO 1110. Drying the specimens was performed in an oven at 80 °C, whereas conditioning the specimens to a state of moisture saturation occurred in an environmental chamber at 70 °C and 62% relative humidity. The glass transition temperature of the investigated PA6 in completely dry state was measured by means of differential scanning  
75 calorimetry on a DSC 204 F1 Phoenix<sup>®</sup> and was found to be 67 °C. Cutting the specimens to the correct dimensions, suitable for carrying out the material characterisation, was performed by waterjet cutting to prevent thermally loading the specimens and altering the degree of crystallinity prior to testing.

### *2.1. UD carbon-fibre reinforced PA6*

80 Specimens were taken from UD laminates that had been produced with Celstran<sup>®</sup> CFR-TP PA6-CF60-01 from Celanese Chemical Europe GmbH; a carbon fibre-reinforced UD tape with PA6 as matrix. The manufacturing of the laminates was carried out at the Fraunhofer IGCV in Augsburg, Germany. The UD tapes had been stacked unidirectionally with a FiberForge<sup>®</sup> Relay 2000 and were consolidated by means of hot compression moulding after  
85 infrared pre-heating. The pre-heating was performed to reduce the total time required for consolidation. A total of 14 layers of UD tape had been used to create the UD laminates and resulted in a nominal thickness of 1.7 mm. The fibre volume content of the produced UD laminates was analysed by matrix burn-off in combination with thermogravimetric analysis (TGA) and yielded a value of 47.8% ±0.2%. The short-term modulus of the UD laminates  
90 were tested in both longitudinal- and transverse directions according to DIN EN ISO 527-4 as preliminary research. The results are shown in Table 1.

## 2.2. Dilatometer experiments

The thermal expansion of the UD laminate was investigated on a Netzsch DIL 402 C dilatometer. This dilatometer has a strain measurement resolution of 0.625  $nm$  and the specimens were cut to a size of 100 x 8 x 1.7  $mm^3$ . All specimens concerning the dilatometer experiments had been conditioned to a dry state to eliminate the effect of hygroscopic shrinkage when subjecting the specimens to the temperature profile of interest. A heating- and cooling rate of 2  $^{\circ}C/min$  were chosen for a temperature range from 25  $^{\circ}C$  to 200  $^{\circ}C$ . The results of the measurements are strain- and temperature as a function of time. Eq. (1) is used to determine the coefficients of thermal expansion [43].

$$\begin{aligned}\alpha_{11} &= \frac{\partial \varepsilon_{11}}{\partial T} \\ \alpha_{22} &= \frac{\partial \varepsilon_{22}}{\partial T}\end{aligned}\tag{1}$$

It is noted that these are tangential coefficients. UD specimens have been measured for elongation in both 0 $^{\circ}$ - and 90 $^{\circ}$  directions. The applied temperature profile and the measured strains are shown in Fig. 1 and Fig. 2 for the 0 $^{\circ}$ - and 90 $^{\circ}$  fibre directions, respectively.

## 2.3. Micrometer measurements and weighings

The hygroscopic expansion of the UD laminate was analysed in both 0 $^{\circ}$ - and 90 $^{\circ}$  directions by carrying out micrometer measurements and weighings on an analytical scale. The utilised micrometer and analytical scale were the Atorn Keeptronic with a resolution of 0.01  $mm$  and a VWR LA Series with a resolution of 0.1  $mg$ , respectively. Three specimens for both measurement directions with dimensions of 100 x 8 x 1.7  $mm^3$  were first conditioned to a dry state before placing them in the environmental chamber to absorb moisture. Initial weight- and length measurements were carried out to obtain reference values for the completely dry UD laminate. Two measurements were taken on the first day after which the interval was changed to once per day until moisture saturation was observed. Eq. (2) is applied to calculate the coefficients of moisture expansion (CMEs).

$$\begin{aligned}\beta_{11} &= \frac{\partial \varepsilon_{11}}{\partial M} \\ \beta_{22} &= \frac{\partial \varepsilon_{22}}{\partial M}\end{aligned}\tag{2}$$

115 The moisture content that is indicated with  $M$  in Eq. (2) was determined with the weight measurements of the specimens as shown in Eq. (3). In Eq. (3),  $W(t)$  and  $W_0$  denote the mass at moment  $t$  in time and the initial dry weight, respectively.

$$M(t) = \frac{W(t) - W_0}{W(t)}\tag{3}$$

#### 2.4. Thermogravimetric analysis

The rate of moisture diffusion was assessed by performing thermogravimetric analysis on  
 120 a Netzsch TG 209 F1 Libra and determining diffusion coefficients afterwards. The specimens that were investigated by means of TGA were first conditioned to a state of moisture saturation. The decreasing weight of the specimens was then measured as they were subjected to an ambient air with temperature values of 80 °C, 120 °C, 150 °C, and 200 °C. The coefficients of diffusion have been determined through the application of an equation that is valid for  
 125 one-dimensional mass diffusion. Hence, the cutting edges of the specimens were sealed to minimise moisture egress through these sides. The weight loss for each specimen can be computed with Eq. (4) and is required for the determination of the diffusion coefficients.

$$G(t) = \frac{W(t) - W_0}{W_\infty - W_0}\tag{4}$$

The symbols  $W_0$  and  $W_\infty$  in Eq. (4) represent the mass of the specimen at the start and end of the TGA measurement, respectively. The value of  $W_\infty$  is identical to the completely  
 130 dry mass of the specimen. The weight loss can be plotted as a function of time and was fitted with the expression shown in Eq. (5), again noting that this expression is only valid for one-dimensional diffusion through an infinitely large plate of which the concentration at the surfaces are kept constant [44, 22]. The only fitting parameter in this expression is the

diffusion coefficient, denoted with  $D$ . The distance of diffusion is governed by  $l$  in Eq. (5) and was taken to be equal to the half-thickness of the specimen due to moisture egress out of both major surfaces of the specimens.

$$G(t) \approx 1 - \frac{8}{\pi^2} \sum_{k=0}^N \frac{1}{(2k+1)^2} \cdot e^{-(2k+1)^2 \pi^2 D \cdot t \cdot l^{-2}} \quad (5)$$

Fitting the weight loss data to Eq. (5) yields diffusion coefficients that correspond to the particular temperature of the corresponding TGA measurement. The Arrhenius equation, displayed in Eq. (6), was used to fit the discrete set of diffusion coefficients to obtain a continuous function of the diffusion coefficient for the entire temperature range [45]. The symbols  $D_0$  and  $E_A$  in Eq. (6) represent the frequency factor and activation energy, respectively.

$$D(T) = D_0 \cdot e^{\frac{E_A}{R \cdot T}} \quad (6)$$

### 2.5. Dynamic mechanical analysis

The stress relaxation behaviour of the UD laminate was analysed by means of DMA on a Netzsch EPLEXOR 500 N. Specimens were trimmed to a size of 80 x 10 x 1.7  $mm^3$  to facilitate a tensile measuring mode. Frequency sweep measurements were performed for a temperature range of 20 °C to 220 °C with a step size of 10 °C. The measured frequencies range from 0.3 Hz to 30 Hz with 8 steps per decade. A trade-off was made here between the duration of the measurement and not damaging the specimen. A hold period of 20 minutes was included between consecutive frequency sweeps to ensure thermal stability inside the DMA test chamber. The stress relaxation was expected to be most significant in 90° direction and DMA analysis was thus only conducted in this direction.

The objective of the DMA was to obtain the transverse relaxation modulus at one specific reference temperature. A mastercurve was constructed for the storage modulus by shifting the individual measurements of the storage modulus on the logarithmic time scale to form one continuous curve, applying the principle of TTS [42]. A reference temperature of 20 °C was chosen for the construction of the mastercurve. The shift factors required for the

construction of the mastercurve also provide quantitative information on how temperature influences the rate of stress relaxation. The objective simulation covers a large temperature range and thus the correct modelling of the temperature-dependent rate of stress relaxation is important to predict accurate deformations. The mastercurve is shown in Fig. 3 and was fitted to a generalised Maxwell model which was formulated in the frequency domain as shown in Eq. (7) [46].

$$E'(\omega) = E'_\infty + \sum_{i=1}^N \frac{E'_i \omega^2 + \tau_i^2}{1 + \omega^2 \tau_i^2} \quad (7)$$

The symbols  $E'_\infty$ ,  $E'_i$ , and  $\tau_i$  denote the long-term modulus and the modulus and relaxation time of the  $i^{\text{th}}$  Maxwell element. The values of the relaxation time of all Maxwell elements were kept constant and evenly spaced on the logarithmic scale. Fitting the moduli of the Maxwell elements was performed with the genetic algorithm method that is provided in the Global Optimization Toolbox in MATLAB. Utilising 32 Maxwell elements led to a root-mean-square (RMS) error of 26.7 MPa. The RMS error has a magnitude of 4.9% of the smallest measured storage modulus and the fit shown in Fig. 4 is thus considered to be satisfactory. The values of  $\tau_i$  and the corresponding values of  $E'_i$  can be used in the generalised Maxwell element formulated in the time domain, Eq. (8). The obtained curve from Eq. (8) represents the relaxation modulus of the UD laminate in 90° direction.

$$E_{22}(t) = E'_\infty + \sum_{i=1}^N E'_i e^{-t/\tau_i} \quad (8)$$

The time shift factors that were obtained by constructing the mastercurve of the storage modulus are utilised to fit the Williams-Landel-Ferry (WLF) equation and analyse the temperature-dependency of the stress relaxation behaviour. The WLF equation is shown in Eq. (9) in which the terms  $C_1$  and  $C_2$  denote the fitting parameters. The symbols  $a_T$  and  $T_0$  denote the time shift factors and the reference temperature, respectively.

$$\log a_T(T) = -\frac{C_1 (T - T_0)}{C_2 + T - T_0} \quad (9)$$

### 2.6. Digital image correlation

Quasi-static tensile tests were performed to obtain the major Poisson's ratio of UD specimens at room temperature. The specimens and testing conditions were chosen to be in agreement with DIN EN ISO 527-4. The dimensions of the specimen measured  $250 \times 15 \times 1.7 \text{ mm}^3$  and the crosshead speed was set to  $2 \text{ mm}\cdot\text{min}^{-1}$ . End tabs of cross-ply GFRP with an orientation of  $\pm 45^\circ$  were applied to increase gradual load introduction and reduce the chances of damaging the specimen in the clamping area. A Zwick/Roell Z100 universal testing machine was used in combination with digital image correlation (DIC) to measure the longitudinal- and transverse strains. The DIC setup included the ARAMIS system with the Deformation 2.3M sensor that has a resolution of  $1936 \times 1216$ . The utilised lens allowed a measuring volume of  $140 \times 95 \times 90 \text{ mm}^3$  and was calibrated at a temperature of  $23.0 \text{ }^\circ\text{C}$  with a camera angle of  $25.492^\circ$ . A picture of the experimental setup for the DIC measurement is shown in Fig. 5. The major Poisson's ratio was evaluated for six specimens at longitudinal strain values of  $0.4\%$  and  $0.5\%$  with Eq. (10).

$$\nu_{12} = -\frac{\varepsilon_{22}}{\varepsilon_{11}} \quad (10)$$

## 3. Results and discussion

### 3.1. Coefficients of thermal expansion

The CTEs that have been calculated with Eq. (1) are shown in Fig. 6 and Fig. 7 for  $0^\circ$ - and  $90^\circ$  fibre orientations, respectively. The variation between the CTEs for heating and cooling originates from two phenomena that are present because of the application of the thermal loading. It is assumed that the transition of the PA6 crystals from  $\gamma$ -form to  $\alpha$ -form is one of the reasons for the increase in density of the laminate. This assumption is based on the relatively low cooling rates in the dilatometer tests which favours the presence of polymer crystals with an  $\alpha$ -form as opposed to a  $\gamma$ -form [28]. Secondly, recrystallisation is activated

as the specimens are heated above the glass transition temperature. Both phenomena would explain the decline in strain during both temperature hold periods in the curve that is depicted in Fig. 2 for 90° direction. Furthermore, these phenomena result in a net shrinkage that can be observed by the negative strain values shown at the end of the cooling phases in Fig. 2.

205 Both phenomena produce differences in CTEs for the heating- and cooling phases, as shown in Fig. 7. It is remarkable that the strain of the UD laminate in 0° direction, shown in Fig. 1, does not return to zero after cooling. This behaviour is assumed to be caused by the fibres as the strain in this direction is highly fibre-dominant due to the high stiffness of the fibres in comparison to the matrix. The importance of determining separate CTEs for heating- and

210 cooling phases for accurate simulation purposes is again noted.

### 3.2. *Coefficients of moisture expansion*

The measured hygroscopic strain is plotted versus the moisture concentration of the specimens that have been weighed for the determination of the CMEs in Fig. 8. The results of the 0°- and 90° fibre directions are shown on the left- and right hand sides, respectively,

215 with corresponding CMEs of  $5.58e^{-3}$  and  $4.26e^{-1}$ . These are determined by means of a linear fit through the origin. It is noted that the degree of experimental scatter is large for the measurements in 0° direction. The scatter is caused by measurement error that is introduced by the resolution of the micrometer in combination with the relatively small hygroscopic strains in 0° direction.

### 220 3.3. *Diffusion coefficients*

Fig. 9 displays the fitted Arrhenius function, of which the expression is shown in Eq. (6), to the determined diffusion coefficients (See Section 2.4). It is noted that the high goodness of fit indicates that the Arrhenius equation provides an excellent method of describing the temperature dependency of the one-dimensional diffusion coefficient.

### 225 3.4. *Stress relaxation behaviour*

The relaxation curve, that is constructed with the moduli of the Maxwell elements in Eq. (7), is displayed in Fig. 10. It is noted that the relaxation curve is valid only for the reference temperature of 20 °C. The resulting instantaneous modulus of the relaxation curve

is in proper agreement with the values measured by quasi-static tensile tests carried out  
230 at room temperature. The instantaneous modulus that was obtained from the quasi-static  
tensile tests was calculated with the stress values measured at 0.05%- and 0.25% strain, in  
agreement with DIN EN ISO 527-4. The specimen relaxes during the strain application, which  
takes approximately 15 seconds, and this explains the discrepancy between the measured  
instantaneous modulus with quasi-static tensile tests and the predicted instantaneous modulus  
235 by means of DMA. The temperature dependency of the transverse relaxation modulus can  
be described by means of the WLF equation, given in Eq. (9). The coefficients  $C_1$  and  $C_2$  in  
Eq. (9) have been determined by fitting the WLF equation to the time shift factors obtained  
from applying the TTS to construct the mastercurve of the storage modulus. This fit is shown  
in Fig. 11 and the values for  $C_1$  and  $C_2$  are 69.85 and 254 °C, respectively.

### 240 3.5. Major Poisson's ratio

The values of the major Poisson's ratio that had been determined for six specimens at  
strain values of 0.4% and 0.5% are shown in Table 2. The average major Poisson's ratio of all  
measurements is equal to 0.400 and the standard deviation is found to be 0.024. It is observed  
that the major Poisson's ratio decreases at higher strain magnitudes due to relaxation of the  
245 matrix constituent.

## 4. Conclusion

The hygrothermal viscoelastic material behaviour of UD laminates of continuous carbon-fibre  
reinforced PA6 was analysed by means of various experiments. Thermal- and hygroscopic  
expansion behaviour was measured by performing dilatometer experiments and micrometer  
250 measurements in combination with weighing, respectively. The thermal- and hygroscopic  
expansion was quantified by the determination of coefficients of thermal- and -hygroscopic  
expansion, respectively. A distinct post-shrinkage was observed for the UD laminate with  
a fibre orientation of 90° and also the UD laminate with a fibre orientation of 0° did not  
return to zero strain after removal of thermal loading. The rate of moisture diffusion out of  
255 the moisture saturated specimens that were dried at various constant temperature conditions  
was investigated by TGA. The Arrhenius equation was used to describe the temperature  
dependency of the experimentally obtained diffusion coefficients and a proper fit to the

experimental data was obtained. The stress relaxation behaviour in transverse direction of the UD laminate was measured by multiple frequency sweeps under isothermal conditions with  
260 DMA. Fitting the constructed mastercurve by a generalised Maxwell model with 32 terms yielded a RMS error of 4.9% of the smallest measured storage modulus. The WLF equation was utilised to describe the temperature-dependency of the relaxation behaviour. Finally, DIC was applied to quasi-static tensile tests to identify the major Poisson's ratio of the UD laminate at room temperature to be 0.400.

265 It was concluded that the post-shrinkage and temperature-dependent relaxation behaviour of the studied material impose challenges for use in structural automotive applications and therefore demand further investigation to validate the accuracy of simulation approaches. The present material characterisation will hence be used for numerical analyses of the influence of the automotive painting process on the deformation behaviour of multi-directional laminates.

## 270 **References**

- [1] Stenbeck W, Schultze D, Kroll L, Nendel S, Nestler D, Zopp C. Ready for Large-Scale Production. *Kunststoffe International*. 2016;106:68–70.
- [2] Esnaola A, Elguezabal B, Aurrekoetxea J, Gallego I, Ulacia I. Optimization of the Semi-Hexagonal Geometry of a Composite Crush Structure by Finite Element Analysis.  
275 *Composites Part B*. 2016;93:56–66.
- [3] Althammer F, Iwan S, Mueller S, Troeltzsch J, Kroll L. Simulating the Forming of Thermoplastic, Fibre Reinforced Plastics - Demonstrated for a Side Impact Protection Beam. *International Journal of Applied Sciences*. 2017;10(2):133–143.
- [4] Mallick PK. *Fiber-Reinforced Composites: Materials, Manufacturing, and Design*. 3rd  
280 ed. Taylor & Francis Group, LLC.; 2007.
- [5] Tomioka M, Ishikawa T, Okuyama K, Tanaka T. Recycling of Carbon-Fiber-Reinforced Polypropylene Prepreg Waste Based on Pelletization Process. *Journal of Composite Materials*. 2017;51(27):3847–3858.
- [6] Mazumdar SK. *Composites Manufacturing: Materials, Product, and Process*. 1st ed.  
285 CRC Press LLC; 2002.

- [7] Miller L, Soulliere K, Sawyer-Beaulieu S, Tseng S, Tam E. Challenges and Alternatives to Plastics Recycling in the Automotive Sector. *Materials*. 2014;7:5883–5902.
- [8] Buekens A, Zhou X. Recycling Plastics from Automotive Shredder Residues: A Review. *Journal of Material Cycles and Waste Management*. 2014;16:398–414.
- 290 [9] Vieille B, Casado VM, Bouvet C. Influence of Matrix Toughness and Ductility on the Compression-After-Impact Behavior of Woven-Ply Thermoplastic and Thermosetting-Composites: A Comparative Study. *Composite Structures*. 2014;110:207–218.
- [10] Fernandez-Villegas I, Vizcaino Rubio P. On Avoiding Thermal Degradation During  
295 Welding of High-Performance Thermoplastic Composites to Thermoset Composites. *Composites: Part A*. 2015;77:172–180.
- [11] Grätzl T, Schramm N, Kroll L. Influence of the Cathodic Dip Painting Process on Fibre-Reinforced Thermoplastic Composites. In: 3rd International Conference & Exhibition on Thermoplastic Composites; 2016. p. 33–36.
- 300 [12] Boccardi S, Meola C, Carlomagno GM, Sorrentino L, Simeoli G, Russo P. Effects of Interface Strength Gradation on Impact Damage Mechanisms in Polypropylene/Woven Glass Fabric Composites. *Composites Part B*. 2016;90:179–187.
- [13] Pramanik A, Basak AK, Dong Y, Sarker PK, Uddin MS, Littlefair G, et al. Joining of Carbon Fibre Reinforced Polymer (CFRP) Composites and Aluminium Alloys - A  
305 Review. *Composites: Part A*. 2017;101:1–29.
- [14] VDI. Emission Control - High-Volume Car Body Painting Plants. VDI Commission on Air Pollution; 2013. 3455.
- [15] Streitberger HJ, Dossel KF. *Automotive paints and coatings*. 2nd ed. John Wiley & Sons; 2008.
- 310 [16] Hufenbach W, Kroll L. Laminated Cylindrical Shells Under Mechanical and Hygro-Thermal Loads. *Advances in Engineering Software*. 1995;23:83–88.

- [17] Hufenbach W, Kroll L. Design and Construction of Hygro-Thermally Stable Shells. *Mechanics of Composite Materials*. 1996;31(5):498–502.
- [18] Arhant M, Le Gac PY, Le Gall M, Burtin C, Briançon C, Davies P. Effect of Sea  
315 Water and Humidity on the Tensile and Compressive Properties of Carbon-Polyamide 6  
Laminates. *Composites: Part A*. 2016;91:250–261.
- [19] Sachs U, Akkerman R. Viscoelastic Bending Model for Continuous Fiber-Reinforced  
Thermoplastic Composites in Melt. *Composites Part A: Applied Science and  
Manufacturing*. 2017;100:333–341.
- 320 [20] Yabu T, Yasuhara S, Kashiwagi M. Development of GF RTP Crush Box with  
Consideration of Use Environment and Effect of Fiber Orientation. *SAE International  
Journal of Materials and Manufacturing*. 2017;10:191–197.
- [21] Joannès S, Mazé L, Bunsell AR. A Concentration-Dependent Diffusion Coefficient Model  
for Water Sorption in Composite. *Composite Structures*. 2013;108:111–118.
- 325 [22] Joannès S, Mazé L, Bunsell AR. A Simple Method for Modeling the  
Concentration-Dependent Water Sorption in Reinforced Polymeric Materials.  
*Composites: Part B*. 2014;57:219–227.
- [23] Broudin M, Le Gac PY, Le Saux V, Champy C, Robert G, Charrier P, et al. Water  
Diffusivity in PA66: Experimental Characterization and Modeling Based on Free Volume  
330 Theory. *European Polymer Journal*. 2015;67:326–334.
- [24] Kovács JG, Solymossy B. Effect of Glass Bead Content and Diameter on Shrinkage and  
Warping of Injection-Molded PA6. *Polymer Engineering & Science*. 2009;49:2218–2224.
- [25] Mehat NM, Kamaruddin S, Othman AR. Optimized Injection Molding of Unfilled and  
Glass Filled PA6 Gears. *International Journal of Manufacturing*. 2014;2014:1–8.
- 335 [26] Sang L, Wang Y, Chen G, Liang J, Wei Z. A Comparative Study of the Crystalline  
Structure and Mechanical Properties of Carbon Fiber/Polyamide 6 Composites Enhanced  
with/without Silane Treatment. *RSC Advances*. 2016;6:107739–107747.

- [27] Fornes TD, Paul DR. Crystallization Behavior of Nylon 6 Nanocomposites. *Polymer*. 2003;44:3945–3961.
- 340 [28] Fereydoon M, Tabatabaei SH, Ajji A. Rheological, Crystal Structure, Barrier, and Mechanical Properties of PA6 and MXD6 Nanocomposite Films. *Polymer Engineering & Science*. 2014;54:2461–2706.
- [29] Heinle M, Drummer D. Temperature-Dependent Coefficient of Thermal Expansion (CTE) of Injection Molded, Short-Glass-Fiber-Reinforced Polymers. *Polymer*  
345 *Engineering and Science*. 2015;55:2661–2668.
- [30] Baran I, Cinar K, Ersoy N, Akkerman R, Hattel JH. A Review on the Mechanical Modeling of Composite Manufacturing Processes. *Archives of Computational Methods in Engineering*. 2017;24:365–395.
- [31] Gabrion X, Placet V, Trivaudey F, Boubakar L. About the Thermomechanical Behaviour of a Carbon Fibre Reinforced High-Temperature Thermoplastic Composite. *Composites Part B*. 2016;95:386–394.  
350
- [32] Karsli NG, Aytac A. Tensile and Thermomechanical Properties of Short Carbon Fiber Reinforced Polyamide 6 Composites. *Composites: Part B*. 2013;51:270–275.
- [33] Rouleau L, Pirk R, Pluymers B, Desmet W. Characterization and Modeling of the  
355 Viscoelastic Behaviour of a Self-Adhesive Rubber Using Dynamic Mechanical Analysis Tests. *Journal of Aerospace Technology and Management*. 2015;7(2):200–208.
- [34] Ropers S, Kardos M, Osswald TA. A Thermo-Viscoelastic Approach for the Characterization and Modeling of the Bending Behavior of Thermoplastic Composites. *Composites: Part A*. 2016;90:22–32.
- 360 [35] Botelho EC, Rezende MC. Monitoring of Carbon Fiber/Polyamide Composites Processing by Rheological and Thermal Analyses. *Polymer-Plastics Technology and Engineering*. 2006;45:61–69.
- [36] Melo JDD, Radford DW. Viscoelastic Characterization of Transversely Isotropic Composite Laminae. *Journal of Composite Materials*. 2003;37(2):129–145.

- 365 [37] Ma X, Jansen KMB, Ernst LJ, van Driel WD, van der Sluis O, Zhang GQ. A New Method  
to Measure the Moisture Expansion in Plastic Packaging Materials. In: Proceedings of  
the 59th Electronic Components and Technology Conference 2009 (ECTC 2009). IEEE;  
2009. p. 1271–1276.
- [38] Ascione L, Berardi VP, D’Aponte A. Long-Term Behavior of PC Beams Externally  
370 Plated with Prestressed FRP Systems: A Mechanical Model. *Composites: Part B*.  
2011;42:1196–1201.
- [39] Berardi VP, Mancusi G. Time-Dependent Behavior of Reinforced Polymer Concrete  
Columns under Eccentric Axial Loading. *Materials*. 2012;5:2342–2352.
- [40] Berardi VP, Mancusi G. A Mechanical Model for Predicting the Long Term Behavior of  
375 Reinforced Polymer Concretes. *Mechanics Research Communications*. 2013;50:1–7.
- [41] Berardi VP, Perrella M, Feo L, Cricrì G. Creep Behavior of GFRP Laminates and  
Their Phases: Experimental Investigation and Analytical Modeling. *Composites Part B*.  
2017;122:136–144.
- [42] Gutierrez-Lemini D. *Engineering Viscoelasticity*. 1st ed. Boston, MA: Springer US; 2014.
- 380 [43] Kollár LP, Springer GS. *Mechanics of Composite Structures*. 1st ed. Cambridge  
University Press; 2003.
- [44] Shen CH, Springer GS. Moisture Absorption and Desorption of Composite Materials.  
*Journal of Composite Materials*. 1976;10:2–20.
- [45] Arrhenius S. On the Reaction Velocity of the Inversion of Cane Sugar by Acids. *Zeitschrift*  
385 *für Physikalische Chemie*. 1889;4:226.
- [46] Park SW, Schapery RA. Methods of Interconversion Between Linear Viscoelastic Material  
Functions. Part I - A Numerical Method Based on Prony Series. *International Journal*  
*of Solids and Structures*. 1999;36:1653–1675.

**Fig. 1.** Applied temperature profile for dilatometer experiment and  $0^\circ$  strain measurement.

**Fig. 2.** Applied temperature profile for dilatometer experiment and  $90^\circ$  strain measurement.

**Fig. 3.** Constructed mastercurve of storage modulus obtained from DMA measurement in  $90^\circ$  direction.

**Fig. 4.** Fitted generalised Maxwell model to the mastercurve shown in Fig. 3.

**Fig. 5.** Experimental setup for measuring the major Poisson's ratio by means of DIC.

**Fig. 6.** Calculated tangential CTEs of the dry composite material in  $0^\circ$  direction for two heat cycles.

**Fig. 7.** Calculated tangential CTEs of the dry composite material in  $90^\circ$  direction for two heat cycles.

**Fig. 8.** Strain and moisture concentration results of the micrometer measurements and weighings, including the determined coefficients of moisture expansion.

**Fig. 9.** Fitted Arrhenius curve that describes the diffusion coefficient as a function of temperature.

**Fig. 10.** Resulting relaxation curve from the fitting parameters of the generalised Maxwell model to fit the mastercurve shown in Fig. 4.

**Fig. 11.** Fitted WLF equation to describe the time shift factors as a function of temperature.

**Table 1.** Experimentally determined short-term properties of Celstran<sup>®</sup> CFR-TP PA6-CF60-01 at room temperature.

<b>Specimen</b>	<b><math>E_{11}</math></b>	<b>Specimen</b>	<b><math>E_{22}</math></b>
1	100.05 GPa	6	4.23 GPa
2	107.20 GPa	7	4.43 GPa
3	109.75 GPa	8	4.14 GPa
4	110.32 GPa	9	4.45 GPa
5	102.34 GPa	10	4.21 GPa

**Table 2.** Major Poisson's ratio values of Celstran<sup>®</sup> CFR-TP PA6-CF60-01 measured with DIC at room temperature.

<b>Specimen</b>	<b><math>\nu_{12}</math> at 4% strain</b>	<b><math>\nu_{12}</math> at 5% strain</b>
1	0.382	0.370
2	0.427	0.416
3	0.420	0.418
4	0.392	0.369
5	0.427	0.422
6	0.396	0.362