

Delft University of Technology

Predominant P3-Type Solid-Solution Phase Transition Enables High-Stability O3-Type Na-Ion Cathodes

Guo, Hao; Zhao, Chenglong; Zhou, Dong; Wang, Jianlin; Ma, Xiaobai; Gao, Jianxiang; Jiao, Xuesheng; Hu, Xufeng; Bai, Xuedong; Sun, Kai

DOI 10.1021/acsami.4c02889

Publication date 2024 Document Version Final published version Published in ACS Applied Materials and Interfaces

Citation (APA)

Guo, H., Zhao, C., Zhou, D., Wang, J., Ma, X., Gao, J., Jiao, X., Hu, X., Bai, X., Sun, K., & Chen, D. (2024). Predominant P3-Type Solid-Solution Phase Transition Enables High-Stability O3-Type Na-Ion Cathodes. *ACS Applied Materials and Interfaces*, *16*(21), 27352-27359. https://doi.org/10.1021/acsami.4c02889

Important note

To cite this publication, please use the final published version (if applicable). Please check the document version above.

Copyright

Other than for strictly personal use, it is not permitted to download, forward or distribute the text or part of it, without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license such as Creative Commons.

Takedown policy

Please contact us and provide details if you believe this document breaches copyrights. We will remove access to the work immediately and investigate your claim.

Green Open Access added to TU Delft Institutional Repository

'You share, we take care!' - Taverne project

https://www.openaccess.nl/en/you-share-we-take-care

Otherwise as indicated in the copyright section: the publisher is the copyright holder of this work and the author uses the Dutch legislation to make this work public.

Predominant P3-Type Solid–Solution Phase Transition Enables High-Stability O3-Type Na-Ion Cathodes

Hao Guo,* Chenglong Zhao,* Dong Zhou, Jianlin Wang, Xiaobai Ma, Jianxiang Gao, Xuesheng Jiao, Xufeng Hu, Xuedong Bai, Kai Sun,* and Dongfeng Chen*

Cite This: ACS Appl. Mater. Interfaces 2024, 16, 27352–27359 Read Online



performance. To address such issues, understanding the interplay of the composition, structure, and properties is crucial. Here, we successfully introduced a P-type characteristic into the O3-type layered structure, achieving a P3-dominated solid–solution phase transition upon cycling. This modification facilitated a reversible transformation of the O3–P3–P3' structure with minimal and gradual volume changes. Consequently, the Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode exhibited a specific capacity of approximately 113 mAh/g, coupled with exceptional cycling performance (maintaining over 70% capacity retention after 900 cycles). These findings shed light on the composition–structure–property relationships of Na-ion layered oxides, offering valuable insights for the advancement of Na-ion batteries.



KEYWORDS: Na-ion batteries, O3-type cathode, Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂, P3-dominated phase transition, O3-P3-P3'

1. INTRODUCTION

Li-ion batteries (LIBs) have been widely applied to consumer devices and electric vehicles due to their high energy density and excellent cycling stability.¹ However, the increasing demand and uneven distribution of Li resources hinder the extensive application of LIBs in the field of energy storage, in which cost is the most important factor. Na-ion batteries (SIBs) are expected to be an alternative to LIBs in energy storage systems because of the stable supply and even distribution of Na resources.^{2–4} In the current SIBs, cathode materials play a significant role in energy density, cycling life, and rate property.^{5,6} Therefore, an in-depth investigation into cathode materials and their corresponding reaction mechanisms during (de)sodiation is of great importance for both the engineering and scientific point of view.7-10 Among the reported cathode materials, Na-ion layered transition metal oxides (Na_xTMO_2) have gained significant attention owing to their great compositional diversity, relatively easy preparation process, and highly reversible specific capacity.¹¹⁻¹⁶ O3-type and P2-type Na_xTMO₂ are the widely studied layered structures used for cathode materials, which are composed of TMO_6 octahedra sheets, where Na ions occupy the octahedral (O) and prismatic environment (P) sites between the octahedra sheets, respectively. The figure (e.g., 3 in O3) represents the stacking number of TMO₆ octahedra sheets in a structure cell.¹⁷ Generally, high Na content can screen the electrostatic repulsion effect between the two oxygen sheets,

leading to a reduction in the $d_{(O-Na-O)}$ interlayer space, which contributes to the emergence of an O3-type structure. On the contrary, low Na content leads to a larger $d_{(O-Na-O)}$ interlayer space, therefore promoting the formation of a P2-type structure.^{18,19}

O3-type NaNi_{0.5}Mn_{0.5}O₂ can exhibit high capacity that benefited from high Na content and adequate Ni^{2+/4+} redox couple. Nevertheless, it suffers irreversible phase transformation with great volume variation at elevated cutoff voltages, which is detrimental for cycling stability.^{20,21} The substitution of Ni²⁺ and Mn⁴⁺ with inert and/or active elements (Zn²⁺, Mg²⁺, Ti⁴⁺, Cu²⁺, etc.) can help to suppress the undesirable phase transformation when the voltage exceeds 4 V, consequently elevating the structure stabilization and cycling stability, but at the expense of capacity.^{22,23} Also, it should be mentioned that the long-term cycling stability of layered O3-type oxides can be further improved by limiting the cutoff voltage. As a result, the practical capacity of O3-type oxides^{24–27} is restricted to about 110–130 mAh/g. Therefore, it is clear that an in-depth understanding of the composition–

Received:February 21, 2024Revised:April 30, 2024Accepted:May 9, 2024Published:May 16, 2024



Downloaded via TU DELFT on June 4, 2024 at 12:51:41 (UTC). See https://pubs.acs.org/sharingguidelines for options on how to legitimately share published articles.





Figure 1. Designing the O3-type structure with P-type structural characteristics. (a) Representation of P2-type and O3-type crystal structures. (b) Prediction of phase structure according to the cationic potential. (c and d) XRD data and refinement results of P2-type Na_{0.75}Ni_{0.25}Cu_{0.1}Fe_{0.05}Mn_{0.60}O₂ and O3-type Na_{0.75}Ni_{0.25}Cu_{0.1}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ materials. (e) $d_{(O-Na-O)}$ versus the ratio of $d_{(O-Na-O)}/d_{(O-TM-O)}$ for O3-Na_x[Ni_aCu_bFe_cMn_dTi_e]O₂ and P2-Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.60}O₂.

structure–property of O3-type Na_xTMO_2 contributes to the design of optimal cathodes presenting the desired properties: large capacity, high structural stability, and excellent cycling stability.

In this work, we designed an O3-type layered oxide with a larger $d_{(O-Na-O)}$ interlamellar spacing, featuring a distinctive attribute of P-type structures.²⁸ The incorporation of the P-type characteristic into the O3-type framework led to a brief O3–P3 phase transition and an extended P3-type solid–solution phase transformation during cycling. This design effectively mitigates irreversible phase transitions and minimizes strain induced by volume changes, resulting in outstanding cycling stability and rate capabilities. Notably, the material exhibited a reversible capacity of approximately 113 mAh/g between 2 and 4.2 V, maintaining a remarkable capacity retention of 70% after 900 cycles and a conservation rate of 63% at SC charging/discharging rates.

2. EXPERIMENTAL SECTION

2.2. Material Characterization. X-ray powder diffraction measurements were conducted on an X-ray diffractometer (D8 Advance, equipped with Cu K α radiation, Bruker, Germany) to study the phase purity and phase structure of the obtained materials. In addition, neutron powder diffraction was applied to further verify the crystal structure as well as transition metal ordering. The used facility is a high-resolution powder diffractometer (HRPD, $\lambda = 1.889$ Å),

which is located in the China Advanced Research Reactor (CARR, China Institute of Atomic Energy, China). Electron microscope techniques were used to characterize the microstructure information of samples, as described in the Supporting Information.

2.3. Electrochemical Measurements. The preparation process of positive electrodes, the fabrication procedure, and the measurement method of coin-type cells were in agreement with those reported in the previous work,²⁹ as shown in the Supporting Information.

3. RESULTS AND DISCUSSION

3.1. Compositional Design. The previous work indicated O3- and P2-types can be distinguished according to the ratio of $d_{(O-Na-O)}$ to $d_{(O-TM-O)}$ in a unit cell. It can be found that a precise dividing line to distinguish O3-type and P2-type structures is at ~ 1.62 .³⁰ Therefore, designing an O3-type layered oxide with a big $d_{(O-Na-O)}$ interlamellar spacing, which facilitates the value of $d_{(O-Na-O)}/d_{(O-TM-O)}$ close to the boundary line of the O3- and P2-type structures, can introduce the P-type structural characteristic into the O3-type structure. We speculated that adjusting the P2-type composition with intermediate Na content can pass through the division between O3- and P2-type structures, promoting the attainment of an O3-type structure with P-type structural characteristics. Here, we selected the composition of P2-type Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.6}O₂ as a candidate, considering that the combination of multiple transition metals has a positive effect on Na storage performance. Inspired by the cationic potential method, 31,32 we found that substituting partial Mn⁴⁺ with appropriate Ti⁴⁺ makes the cationic potential (Φ_{cation}) pass though the dividing line between two stacking

www.acsami.org



Figure 2. Structural characterization. NPD pattern and Rietveld refinement, schematic crystal structure, and transition metal arrangement of O3– $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ using (a–c) *R-3m* and (d–f) *C2/m* space groups, respectively. (g and h) High-angle annular dark field and annular light field STEM images and energy dispersive X-ray spectroscopy (EDS) mappings of the $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ sample.

structures, indicating that the adjusted $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ material has an O3-type stacking structure while possessing a characteristic of P-type structures (Figure 1b).

To prove the prediction, we prepared $N a_{0.75} N i_{0.25} C u_{0.10} F e_{0.05} M n_{0.6} O_{2} and$ Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ samples using a hightemperature solid-state method. The phase purity and phase structure of two samples were first analyzed by means of X-ray diffraction (XRD) and Rietveld refinement. As illustrated in Figure 1c, the diffraction peaks of the $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.6}O_2$ sample can be well indexed with the space group of P63/mmc. The relevant P2-type stacking structure, depicted in Figure 1a, was composed of TMO₆ octahedra sheets with oxygen stacking arrangements of ABBA. Na ions occupied the two prismatic environment (P) sites between the octahedra sheets. The Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ sample crystallized to an O3-type structure with repeating ABCABC stacking (Figures 1a and 1d), corresponding to the NaFeO₂ structure with R-3m symmetry. The detailed crystal structure parameters of the $N a_{0\,.\,7\,\,5} \, N \, i_{\,0\,.\,2\,\,5} \, C \, u_{\,0\,.\,1\,\,0} \, F \, e_{\,0\,.\,0\,\,5} \, M \, n_{\,0\,.\,6} \, O_{\,2} \quad a \, n \, d$ $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ samples are displayed in Tables S1 and S2, respectively. These results demonstrated that the $d_{(O-Na-O)}$ interlayer distance of the $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ material was 0.339 nm, larger than those of other high-Na O3-type layered oxides (Figure 1e and Table S4). The resulting value of $d_{(O-Na-O)}$ to d_(O-TM-O) for O3-type Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ was 1.607, which is close to the boundary line of the P2type structure, demonstrating that this O3-type $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ material has P2-like characteristics and may exhibit improved Na storage performance.

crystal structures Τhe o f t h e $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2 \ \ samples \ \ were \ \ further$ characterized by neutron powder diffraction (NPD). It is worth noting that some weak diffraction peaks in the NPD pattern, which were absent in the XRD pattern, cannot be indexed with the R-3*m* space group (Figure 1d and Figure 2a). Instead, good fitting results can be obtained by using the C2/mspace group involving 3d transition metal (TM) ordering (Figure 2d). The relevant crystal structure parameters of the $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2\ material\ obtained\ by$ using R-3m and C2/m space groups are shown in Tables S5 and S6, respectively. As shown in Figures 2e and 2f, in the crystal structure with the C2/m space group, Na atoms occupied two octahedral sites (2d and 4h) between the TMO₂ slabs. Ni/Cu/Fe/Mn/Ti atoms simultaneously occupied two sites (2a and 4g) within the TMO₂ slabs but presented the separately predominant occupations. In other words, most of the Ni, Cu, and Fe atoms were located in 2a sites, while the great mass of Mn and Ti atoms occupied the 4g sites. As a result, the specific transition metal ordering results in the broadened and weak superlattice peaks in the NPD pattern, which cannot be observed in the XRD pattern owing to the similar scattering ability of 3d transition metals with the near atomic number Z. In addition, we also investigated the TM ordering in the Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ sample by using scanning transmission electron microscopy (STEM). Nevertheless, the ordered distribution of TM elements with regular 'bright-bright-dark-bright-bright' arrangements was not visible in STEM images due to the similar atomic numbers between Ni/Cu/Fe/Mn/Ti (Figure 2g).

The crystal structure and element distribution of the $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ sample were also studied using high-resolution transmission electron microscopy (HRTEM). By analyzing the selected area electron diffraction pattern (Figure S1), the diffraction spots correspond to the



Figure 3. Electrochemical performance. (a) Charge-discharge curves and (b) cyclic voltammetry profiles of the O3- $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ cathodes when cycled in the voltage region of 2.0–4.2 V. (c) GITT profiles for the first charging and discharging at 0.1C and (d and e) rate capability of the O3- $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ cathodes at 0.5C and 1C rates, respectively. (h) Comparison of cycling performance with other O3-type cathodes.^{23,24,33-39}

(101) and (012) planes of the crystal structure with the *R*-3*m* space group, respectively, compatible with the results of XRD refinement. As presented in Figure 2g, the distances between the neighboring lattice fringes were 0.549 nm, corresponding to the (003) lattice planes, which was also consistent with the HRTEM result. In addition, energy dispersive X-ray spectroscopy (EDS) mappings (Figure 2h and Figure S1) indicated that the elements in the Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ materials presented a uniform distribution.

3.2. Electrochemical Performance. To investigate the influence of large $d_{(O-Na-O)}$ interlayer distance on the electrochemical property, Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathodes were tested by coin-type half cells. The Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode showed a discharge capacity of 113 mAh/g between 2.0 and 4.2 V at a current density of 12 mA/g (0.1C). Notably, the charge–discharge profiles and CV curves of the

Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathodes displayed high coincidence (Figures 3a and 3b). As shown in Figures 3c and S2, the galvanostatic intermittent titration technique (GITT) measurement indicated t h e that Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode exhibited a high Na-ion diffusion coefficient (stabilizes at $10^{-10} - 10^{-11} \text{ cm}^2/\text{s}$), therefore resulting in improved rate capabilities. As presented in Figures 3d and 3e, the reversible capacities of the Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode were 112, 106, 98, 90, 80, and 70 mAh/g at 0.1C, 0.2C, 0.5C, 1C, 2C, and 5C rates, respectively, demonstrating outstanding rate performance. In addition, it can be clearly seen from Figures 3f and 3g that $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ cathodes have a remarkable cycling performance with 70% capacity retention after 900 cycles at a 1C rate, which is superior to that of other O3-type layered oxides (Figure 3h and Table S7). Consequently, the superior cycling performance and rate



Figure 4. Structural transformation during cycling. (a) In situ XRD patterns of the O3 $-Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ cathode upon cycling. (b) Cell parameter evolution of the O3 $-Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ cathode during charging and discharging.



Figure 5. Performance enhancement mechanism. The (003) peak evolution when the $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ cathode is at the low charging voltage region (a) and the high charging voltage region (b), indicating an O3–P3 phase transition and a P3–P3' phase transition, respectively. (c) The normalized charge profiles of O3-type $Na_x[Ni_aCu_bFe_cMn_dTi_e]O_2$; the black line represents the boundary of capacity stored in O3-type and P3-type regions. (d) The evolution of crystal structure and interlayer distance (1/3 of cell parameter *c*) when the $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ cathode is at different charging states.

c a p a b i l i t i e s o f t h e O 3 - t y p e $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ prove its potential for future application.

3.3. Structural Evolution. To understand the effect of large $d_{(O-Na-O)}$ interlayer space on the structure evolution and electrochemical performance of the O3 – Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode, we conducted in situ XRD measurements during charging and discharging. As shown in Figure 4a, upon initial charging, the (003) diffraction peaks and (101) peaks of the O3-type Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode moved to a lower and a higher 2 θ angle, respectively, suggesting the solid-soluble reaction (Figure 4b). With subsequent charging, the O3-type phase, corresponding to the short low-voltage plateau region in charge-discharge curves (Figure 3a).

Upon further charging, it is noteworthy that the (003) peaks of the P3 phase unexpectedly and gradually moved to higher 2θ angles, demonstrating the gradual decrease of the interlayer distance. This phenomenon is different from those of other O3-type cathode oxides.^{24,40–42} It is generally known that the (003) peaks of the P3 phase will gradually shift to a lower 2θ angle upon the deintercalation of Na⁺, corresponding to the increase of the interlayer distance.^{41,43} Until the end of charging, no new peak was observed and the Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode maintained a P3-type structure but with different cell parameters (Figure 4b). To further confirm the crystal structure of the Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode at high voltage, we performed the ex situ XRD measurements of this cathode when charged to 4 and 4.2 V, respectively. It can be found from Figure S3 that both XRD patterns can be fitted with the R3*m* space group, proving the same P3-type structure. Consequently, we denote this type of structure at high voltage as the P3' type. During discharging, the P3' structure changed back to the initial O3 structure in an opposite way (Figure 4a and Figure 4b), indicating a high reversibility.

3.4. Performance Improving Mechanism. Generally, O3-type cathode oxides usually suffer performance degradation during charging and discharging, resulting from the appearance of a distorted phase and large-volume phase transition during deep desodiation. 20,22,33,44,45 For example, NaNi_{0.5}Mn_{0.5}O₂ exhibited a complicated phase evolution (O3-O3'-P3-P3'-P3") upon deintercalation and intercalation of Na, which has a detrimental influence on the electrochemical performance.²⁰ It is generally appreciated that the appearance of distorted phases including O3' and P3' upon deintercalation and intercalation of Na results from the Jahn-Teller effect of Ni³⁺ and Na⁺/vacancy ordering, which can be suppressed by rational element substitution.^{21,46} As shown in Figures 5a and 5d, in the case of the $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ cathode, any distorted phase including O3' and P3' structures were absent owing to the synergism of multiple 3d transition metals. The reversible O3-P3 phase transformation at the lowvoltage region contributes to the promotion of cycling performance (Figure 5d). In addition, when O3-type cathode oxides are in the state of deep deintercalation of Na, the largevolume phase transition such as P3-O3" frequently occurs.³ The crystal structure of the O3" phase is analogous to that of the initial O3 phase but with a lower interlayer distance. This P3-O3" phase transition is always accompanied by a significant lattice volume change, which will result in structural degradation and cracking generation during repeated charge and discharge, leading to the performance fading.^{22,33,2} Instead of a P3-O3" phase transition at the high-voltage region, a P3-P3' phase transition was present in the case of the Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode (Figures 5b and 5d). Specifically, the lattice volume of the P3 phase decreased slowly upon charging to high voltage (Figure 4b), which facilitates the enhancement of the cycling property when operating at high cutoff voltage. To further prove the benefit of the P3-dominated solid-solution phase transition, we designed a series of layered oxide cathodes with the same transition metal (TM) elements but with different Na content. When designing the TM components, we adopted the approximate ratio of Ti to Mn to reduce the effect of undesirable phase transitions at high voltage. It can be seen from Figure 5c that the proportion of the capacity stored in P3-type region during the electrochemical Na⁺ deintercalation grew linearly with the decrease of Na in $Na_x[Ni_aCu_bFe_cMn_dTi_e]O_2$. As a result, the Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode with the most predominant P3-type solid-solution phase transition showed the best cycling stability and rate capabilities (Figure S4). Moreover, we investigated the structure evolution of NaNi_{0.35}Cu_{0.1}Fe_{0.1}Mn_{0.10}Ti_{0.35}O₂ during charging and discharging via ex situ XRD. As shown in Figure S5, while charging, the structure transformation of the Na-Ni_{0.35}Cu_{0.1}Fe_{0.1}Mn_{0.10}Ti_{0.35}O₂ cathode was similar to that of $Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O_2$ (O3-P3-P3'). However, in the course of discharging, the P3'-type structure changed back to the O3-type structure in an asymmetric way, demonstrating the poor reversibility. Therefore, the Na- $Ni_{0.35}Cu_{0.1}Fe_{0.1}Mn_{0.10}Ti_{0.35}O_2$ material with an asymmetric and O3-dominated phase transition exhibited the worst cycling stability and rate performance. Ultimately, we concluded that

the highly reversible and P3-dominated solid-solution phase transformation with minimal and slow volume change during the charge-discharge course results in the excellent cycling stability and rate capabilities of the Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂ cathode.

4. CONCLUSIONS

In conclusion, we successfully incorporated the P-type characteristic into the O3-type structure through strategic adjustments in composition and the $d_{(O-Na-O)}$ interlayer space. cathode, The denoted a s O 3 – Na_{0.75}Ni_{0.25}Cu_{0.10}Fe_{0.05}Mn_{0.15}Ti_{0.45}O₂, presented remarkable cycling stability, with a capacity retention of 70% after 900 cycles at a current rate of 1C. Additionally, it demonstrated outstanding rate capabilities, with 63% capacity retention even at a high 5C rate. These findings suggest that the exceptional cycling performance and rate capabilities stem from the dominance of the P3-driven solid-solution phase transition and the controlled volume changes during charging and discharging. This study provides valuable insights for the rational development of high-stability O3-type layered oxide cathodes tailored for SIBs.

ASSOCIATED CONTENT

Supporting Information

The Supporting Information is available free of charge at https://pubs.acs.org/doi/10.1021/acsami.4c02889.

The obtained crystal structure parameters via refinement, ICP results, the values of $d_{(O-Na-O)}$ and $d_{(O-Na-O)}/d_{(O-TM-O)}$, HRTEM images, SAED, EDS mappings, Na⁺ diffusivity, ex situ XRD, comparison of cycling stabilities of O3-type layered cathodes at elevated cutoff voltages, and the rate capabilities and cycling performance of Na_x[Ni_aCu_bFe_cMn_dTi_e]O₂ with high Na content (PDF)

AUTHOR INFORMATION

Corresponding Authors

- Hao Guo China Institute of Atomic Energy, Beijing 102413, P. R. China; orcid.org/0000-0003-1764-9589; Email: guohao@ciae.ac.cn
- **Chenglong Zhao** Department of Radiation Science and Technology, Delft University of Technology, Delft 2629JB, Netherlands; Email: c.zhao-1@tudelft.nl
- Kai Sun China Institute of Atomic Energy, Beijing 102413, P. R. China; ⊚ orcid.org/0000-0002-9332-7664; Email: ksun@sina.com
- Dongfeng Chen China Institute of Atomic Energy, Beijing 102413, P. R. China; Email: dfchenciae@126.com

Authors

- **Dong Zhou** School of Advanced Energy, Shenzhen Campus of Sun Yat-Sen University, Shenzhen 518107, P. R. China
- Jianlin Wang State Key Laboratory for Surface Physics, Institute of Physics, Chinese Academy of Sciences, Beijing 100190, P. R. China; orcid.org/0000-0002-1749-4428
- Xiaobai Ma China Institute of Atomic Energy, Beijing 102413, P. R. China
- Jianxiang Gao China Institute of Atomic Energy, Beijing 102413, P. R. China
- Xuesheng Jiao China Institute of Atomic Energy, Beijing 102413, P. R. China

- **Xufeng Hu** China Institute of Atomic Energy, Beijing 102413, P. R. China
- Xuedong Bai State Key Laboratory for Surface Physics, Institute of Physics, Chinese Academy of Sciences, Beijing 100190, P. R. China; orcid.org/0000-0002-1403-491X

Complete contact information is available at: https://pubs.acs.org/10.1021/acsami.4c02889

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

This work is supported by the National Natural Science Foundation of China (Grants 12105372 and 52372211).

REFERENCES

(1) Manthiram, A. A Reflection on Lithium-Ion Battery Cathode Chemistry. *Nat. Commun.* **2020**, *11* (1), 1550.

(2) Hu, Y.-S.; Li, Y. Unlocking Sustainable Na-Ion Batteries into Industry. ACS Energy Lett. 2021, 6 (11), 4115–4117.

(3) Delmas, C. Sodium and Sodium-Ion Batteries: 50 Years of Research. Adv. Energy Mater. 2018, 8 (17), No. 1703137.

(4) Sun, Y.; Shi, P.; Chen, J.; Wu, Q.; Liang, X.; Rui, X.; Xiang, H.; Yu, Y. Development and Challenge of Advanced Nonaqueous Sodium Ion Batteries. *EnergyChem.* **2020**, *2* (2), No. 100031.

(5) Lee, W.; Kim, J.; Yun, S.; Choi, W.; Kim, H.; Yoon, W.-S. Multiscale Factors in Designing Alkali-Ion (Li, Na, and K) Transition Metal Inorganic Compounds for Next-Generation Rechargeable Batteries. *Energy Environ. Sci.* **2020**, *13*, 4406–4449.

(6) Huang, Y.; Zheng, Y.; Li, X.; Adams, F.; Luo, W.; Huang, Y.; Hu, L. Electrode Materials of Sodium-Ion Batteries toward Practical Application. *ACS Energy Lett.* **2018**, *3* (7), 1604–1612.

(7) Ji, H.; Zhai, J.; Chen, G.; Qiu, X.; Fang, H.; Zhang, T.; Huang, Z.; Zhao, W.; Wang, Z.; Chu, M.; Wang, R.; Wang, C.; Li, R.; Zeng, W.; Wang, X.; Xiao, Y. Surface Engineering Suppresses the Failure of Biphasic Sodium Layered Cathode for High Performance Sodium-Ion Batteries. *Adv. Funct. Mater.* **2022**, 32 (12), No. 2109319.

(8) Lamb, J.; Jarvis, K.; Manthiram, A. Molten-Salt Synthesis of O3-Type Layered Oxide Single Crystal Cathodes with Controlled Morphology towards Long-Life Sodium-Ion Batteries. *Small* **2022**, *18* (43), No. 2106927.

(9) Jia, X.-B.; Wang, J.; Liu, Y.-F.; Zhu, Y.-F.; Li, J.-Y.; Li, Y.-J.; Chou, S.-L.; Xiao, Y. Facilitating Layered Oxide Cathodes Based on Orbital Hybridization for Sodium-Ion Batteries: Marvelous Air Stability, Controllable High Voltage, and Anion Redox Chemistry. *Adv. Mater.* **2024**, *36* (15), No. 2307938.

(10) Zhu, X.; Xu, S.-W.; Wang, X.-Z.; Liu, M.; Cheng, Y.; Wang, P.-F. Sodium Composite Oxide Cathode Materials:Phase Regulation, Electrochemical Performance and Reaction Mechanism. *Batteries Supercaps* **2023**, *6* (3), No. e202200473.

(11) Wang, P.-F.; You, Y.; Yin, Y.-X.; Guo, Y.-G. Layered Oxide Cathodes for Sodium-Ion Batteries: Phase Transition, Air Stability, and Performance. *Adv. Energy Mater.* **2018**, *8* (8), No. 1701912.

(12) Ortiz-Vitoriano, N.; Drewett, N. E.; Gonzalo, E.; Rojo, T. High Performance Manganese-Based Layered Oxide Cathodes: Overcoming the Challenges of Sodium Ion Batteries. *Energy Environ. Sci.* **2017**, *10* (5), 1051–1074.

(13) Kubota, K.; Kumakura, S.; Yoda, Y.; Kuroki, K.; Komaba, S. Electrochemistry and Solid-State Chemistry of NaMeO₂ (Me = 3d Transition Metals). *Adv. Energy Mater.* **2018**, 8 (17), No. 1703415.

(14) Wang, Y.; Xiao, R.; Hu, Y. S.; Avdeev, M.; Chen, L. P2-Na_{0.6}[$Cr_{0.6}Ti_{0.4}$]O₂ Cation-Disordered Electrode for High-Rate Symmetric Rechargeable Sodium-Ion Batteries. *Nat. Commun.* **2015**, *6*, 6954.

(15) Yu, Y.; Zhang, J.; Gao, R.; Wong, D.; An, K.; Zheng, L.; Zhang, N.; Schulz, C.; Liu, X. Triggering Reversible Anion Redox Chemistry

in O3-Type Cathodes by Tuning Na/Mn Anti-Site Defects. *Energy Environ. Sci.* **2023**, *16* (2), 584–597.

(16) Li, J.; Hu, H.; Wang, J.; Xiao, Y. Surface Chemistry Engineering of Layered Oxide Cathodes for Sodium-Ion Batteries. *Carbon Neutralization* **2022**, *1* (2), 96–116.

(17) Delmas, C.; Fouassier, C.; Hagenmuller, P. Structural Classification and Properties of the Layered Oxides. *Physica* B+C **1980**, 99 (1-4), 81–85.

(18) Wang, J.; Zhu, Y.-F.; Su, Y.; Guo, J.-X.; Chen, S.; Liu, H.-K.; Dou, S.-X.; Chou, S.-L.; Xiao, Y. Routes to High-Performance Layered Oxide Cathodes for Sodium-Ion Batteries. *Chem. Soc. Rev.* **2024**, *53*, 4230.

(19) Liu, M.; Wu, B.; Si, D.; Dong, H.; Chen, K.; Zheng, L.; Fan, X.-Y.; Yu, L.; Xiao, B.; Chou, S.; Xiao, Y.; Wang, P.-F. Electronic States Tailoring and Pinning Effect Boost High-Power Sodium-Ion Storage of Oriented Hollow P2-Type Cathode Materials. *ACS Appl. Mater. Interfaces* **2023**, *15* (46), 53623–53631.

(20) Komaba, S.; Yabuuchi, N.; Nakayama, T.; Ogata, A.; Ishikawa, T.; Nakai, I. Study on the Reversible Electrode Reaction of $Na_{1-x}Ni_{0.5}Mn_{0.5}O_2$ for a Rechargeable Sodium-Ion Battery. *Inorg. Chem.* **2012**, *51* (11), 6211–6220.

(21) Yu, T.-Y.; Ryu, H.-H.; Han, G.; Sun, Y.-K. Understanding the Capacity Fading Mechanisms of O3-Type $Na[Ni_{0.5}Mn_{0.5}]O_2$ Cathode for Sodium-Ion Batteries. *Adv. Energy Mater.* **2020**, *10* (37), No. 2001609.

(22) Mariyappan, S.; Marchandier, T.; Rabuel, F.; Iadecola, A.; Rousse, G.; Morozov, A. V.; Abakumov, A. M.; Tarascon, J.-M. The Role of Divalent $(Zn^{2+}/Mg^{2+}/Cu^{2+})$ Substituents in Achieving Full Capacity of Sodium Layered Oxides for Na-Ion Battery Applications. *Chem. Mater.* **2020**, 32 (4), 1657–1666.

(23) You, Y.; Xin, S.; Asl, H. Y.; Li, W.; Wang, P.-F.; Guo, Y.-G.; Manthiram, A. Insights into the Improved High-Voltage Performance of Li-Incorporated Layered Oxide Cathodes for Sodium-Ion Batteries. *Chem.* **2018**, *4* (9), 2124–2139.

(24) Guo, H.; Avdeev, M.; Sun, K.; Ma, X.; Wang, H.; Hu, Y.; Chen, D. Pentanary Transition-Metals Na-Ion Layered Oxide Cathode with Highly Reversible O3-P3 Phase Transition. *Chem. Eng. J.* **2021**, *412*, No. 128704.

(25) Yao, H.-R.; Lv, W.-J.; Yin, Y.-X.; Ye, H.; Wu, X.-W.; Wang, Y.; Gong, Y.; Li, Q.; Yu, X.; Gu, L.; Huang, Z.; Guo, Y.-G. Suppression of Monoclinic Phase Transitions of O3-Type Cathodes Based on Electronic Delocalization for Na-Ion Batteries. *ACS Appl. Mater. Interfaces* **2019**, *11* (25), 22067–22073.

(26) Ding, F.; Zhao, C.; Xiao, D.; Rong, X.; Wang, H.; Li, Y.; Yang, Y.; Lu, Y.; Hu, Y.-S. Using High-Entropy Configuration Strategy to Design Na-Ion Layered Oxide Cathodes with Superior Electrochemical Performance and Thermal Stability. *J. Am. Chem. Soc.* **2022**, 144 (18), 8286–8295.

(27) Mu, L.; Xu, S.; Li, Y.; Hu, Y. S.; Li, H.; Chen, L.; Huang, X. Prototype Sodium-Ion Batteries Using an Air-Stable and Co/Ni-Free O3-Layered Metal Oxide Cathode. *Adv. Mater.* **2015**, *27* (43), 6928–6933.

(28) Wang, Q.; Zhou, D.; Zhao, C.; Wang, J.; Guo, H.; Wang, L.; Yao, Z.; Wong, D.; Schuck, G.; Bai, X.; Lu, J.; Wagemaker, M. Fast-Charge High-Voltage Layered Cathodes for Sodium-Ion Batteries. *Nat. Sustain.* **2024**, 7 (3), 338–347.

(29) Guo, H.; Zhao, C.; Gao, J.; Yang, W.; Hu, X.; Ma, X.; Jiao, X.; Yang, J.; Sun, K.; Chen, D. Slight Multielement Doping-Induced Structural Order–Disorder Transition for High-Performance Layered Na-Ion Oxide Cathodes. *ACS Appl. Mater. Interfaces* **2023**, *15* (29), 34789–34796.

(30) Zhao, C.; Avdeev, M.; Chen, L.; Hu, Y.-S. An O3-type Oxide with Low Sodium Content as the Phase-Transition-Free Anode for Sodium-Ion Batteries. *Angew. Chem., Int. Ed.* **2018**, *57* (24), 7056–7060.

(31) Zhao, C.; Wang, Q.; Yao, Z.; Wang, J.; Sánchez-Lengeling, B.; Ding, F.; Qi, X.; Lu, Y.; Bai, X.; Li, B.; Li, H.; Aspuru-Guzik, A.; Huang, X.; Delmas, C.; Wagemaker, M.; Chen, L.; Hu, Y.-S. Rational (32) Wang, Q.; Zhou, Y.; Wang, X.; Guo, H.; Gong, S.; Yao, Z.; Wu, F.; Wang, J.; Ganapathy, S.; Bai, X.; Li, B.; Zhao, C.; Janek, J.; Wagemaker, M. Designing Lithium Halide Solid Electrolytes. *Nat. Commun.* **2024**, *15* (1), 1050.

(33) Ding, F.; Zhao, C.; Zhou, D.; Meng, Q.; Xiao, D.; Zhang, Q.; Niu, Y.; Li, Y.; Rong, X.; Lu, Y.; Chen, L.; Hu, Y.-S. A Novel Ni-Rich O3-Na $[Ni_{0.60}Fe_{0.25}Mn_{0.15}]O_2$ Cathode for Na-Ion Batteries. *Energy Storage Mater.* **2020**, *30*, 420–430.

(34) Zheng, S.; Zhong, G.; McDonald, M. J.; Gong, Z.; Liu, R.; Wen, W.; Yang, C.; Yang, Y. Exploring the Working Mechanism of Li+ in O3-Type $NaLi_{0.1}Ni_{0.35}Mn_{0.55}O_2$ Cathode Materials for Rechargeable Na-Ion Batteries. J. Mater. Chem. A **2016**, 4 (23), 9054–9062.

(35) Hwang, J.-Y.; Yu, T.-Y.; Sun, Y.-K. Simultaneous MgO Coating and Mg Doping of $Na[Ni_{0.5}Mn_{0.5}]O_2$ Cathode: Facile and Customizable Approach to High-Voltage Sodium-Ion Batteries. *J. Mater. Chem. A* **2018**, 6 (35), 16854–16862.

(36) Yu, L.; Chang, Y.-X.; Liu, M.; Feng, Y.-H.; Si, D.; Zhu, X.; Wang, X.-Z.; Wang, P.-F.; Xu, S. O3-Type Na_{0.95}Ni_{0.40}Fe_{0.15}Mn_{0.3}Ti_{0.15}O₂ Cathode Materials with Enhanced Storage Stability for High-Energy Na-Ion Batteries. ACS Appl. Mater. Interfaces **2023**, 15 (19), 23236–23245.

(37) Sun, X.; Jin, Y.; Zhang, C.-Y.; Wen, J.-W.; Shao, Y.; Zang, Y.; Chen, C.-H. Na $[Ni_{0.4}Fe_{0.2}Mn_{0.4-x}Ti_x]O_2$: A Cathode of High Capacity and Superior Cyclability for Na-Ion Batteries. *J. Mater. Chem. A* **2014**, 2 (41), 17268–17271.

(38) Huang, Q.; Feng, Y.; Wang, L.; Qi, S.; He, P.; Ji, X.; Liang, C.; Chen, S.; Zhou, L.; Wei, W. Structure Modulation Strategy for Suppressing High Voltage P3-O1 Phase Transition of O3-Na $Mn_{0.5}Ni_{0.5}O_2$ Layered Cathode. *Chem. Eng. J.* **2022**, 431, No. 133454.

(39) Wang, H.; Gao, X.; Zhang, S.; Mei, Y.; Ni, L.; Gao, J.; Liu, H.; Hong, N.; Zhang, B.; Zhu, F.; Deng, W.; Zou, G.; Hou, H.; Cao, X.; Chen, H.; Ji, X. High-Entropy Na-Deficient Layered Oxides for Sodium-Ion Batteries. *ACS Nano* **2023**, *17* (13), 12530–12543.

(40) Anang, D. A.; Park, J.-H.; Bhange, D. S.; Cho, M. K.; Yoon, W. Y.; Chung, K. Y.; Nam, K.-W. O3-Type Layer-Structured $Na_{0.8}[Ni_{1/5}Fe_{1/5}Co_{1/5}Mn_{1/5}Ti_{1/5}]O_2$ as Long Life and High Power Cathode Material for Sodium-Ion Batteries. *Ceram. Int.* **2019**, *45* (17, Part B), 23164–23171.

(41) Yue, J.-L.; Yin, W.-W.; Cao, M.-H.; Zulipiya, S.; Zhou, Y.-N.; Fu, Z.-W. A Quinary Layer Transition Metal Oxide of Na- $Ni_{1/4}Co_{1/4}Fe_{1/4}Mn_{1/8}Ti_{1/8}O_2$ as a High-Rate-Capability and Long-Cycle-Life Cathode Material for Rechargeable Sodium Ion Batteries. *Chem. Commun.* **2015**, *51* (86), 15712–15715.

(42) Tian, K.; He, H.; Li, X.; Wang, D.; Wang, Z.; Zheng, R.; Sun, H.; Liu, Y.; Wang, Q. Boosting Electrochemical Reaction and Suppressing Phase Transition with a High-Entropy O3-Type Layered Oxide for Sodium-Ion Batteries. *J. Mater. Chem. A* **2022**, *10* (28), 14943–14953.

(43) Du, X.-Y.; Meng, Y.; Yuan, H.; Xiao, D. High-Entropy Substitution: A Strategy for Advanced Sodium-Ion Cathodes with High Structural Stability and Superior Mechanical Properties. *Energy Storage Mater.* **2023**, *56*, 132–140.

(44) Wang, Q.; Mariyappan, S.; Vergnet, J.; Abakumov, A. M.; Rousse, G.; Rabuel, F.; Chakir, M.; Tarascon, J.-M. Reaching the Energy Density Limit of Layered O3-NaNi_{0.5}Mn_{0.5}O₂ Electrodes via Dual Cu and Ti Substitution. *Adv. Energy Mater.* **2019**, *9* (36), No. 1901785.

(45) Kubota, K.; Fujitani, N.; Yoda, Y.; Kuroki, K.; Tokita, Y.; Komaba, S. Impact of Mg and Ti Doping in O3 Type NaNi_{1/2}Mn_{1/2}O₂ on Reversibility and Phase Transition during Electrochemical Na Intercalation. *J. Mater. Chem. A* **2021**, *9*, 12830–12844.

(46) Wang, P. F.; Yao, H. R.; Liu, X. Y.; Zhang, J. N.; Gu, L.; Yu, X. Q.; Yin, Y. X.; Guo, Y. G. Ti-Substituted $NaNi_{0.5}Mn_{0.5-x}Ti_xO_2$ Cathodes with Reversible O3-P3 Phase Transition for HighPerformance Sodium-Ion Batteries. Adv. Mater. 2017, 29 (19), No. 1700210.

Research Article

www.acsami.org