

Partitioning kinetics of alloying elements in a medium Mn steel during Q&P treatments using phase field modelling

Ayenampudi, Sudhindra; Celada-Casero, Carola; Mecozzi, Pina; Sietsma, Jilt; Santofimia, Maria Jesus

Publication date

2018

Document Version

Final published version

Citation (APA)

Ayenampudi, S., Celada-Casero, C., Mecozzi, P., Sietsma, J., & Santofimia, M. J. (2018). *Partitioning kinetics of alloying elements in a medium Mn steel during Q&P treatments using phase field modelling*. THERMEC 2018: International Conference on processing & manufacturing of advanced materials, Paris, France.

Important note

To cite this publication, please use the final published version (if applicable).
Please check the document version above.

Copyright

Other than for strictly personal use, it is not permitted to download, forward or distribute the text or part of it, without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license such as Creative Commons.

Takedown policy

Please contact us and provide details if you believe this document breaches copyrights.
We will remove access to the work immediately and investigate your claim.

Partitioning kinetics of alloying elements in a medium Mn steel during Q&P treatments using phase field modelling

Sudhindra Ayenampudi, C. Celada-Casero, M.G. Mecozzi, J. Sietsma, M.J. Santofimia

Department of Materials Science and Engineering, Delft University of Technology, Mekelweg 2, 2628 CD Delft, The Netherlands

S.Ayenampudi@tudelft.nl, C.CeladaCasero@tudelft.nl, M.G.Mecozzi@tudelft.nl,
J.Sietsma@tudelft.nl, M.J.SantofimiaNavarro@tudelft.nl

The Quenching and Partitioning process provides steels with an improved combination of strength and ductility when compared with other advanced high strength steels. This processing route involves several steps in which a complex microstructural development takes place. The microstructural development during the Q&P process has been studied in the past with 2D phase field modelling including only aspects related to carbon partitioning, where the partitioning kinetics of substitutional alloying elements have been neglected. This work investigates, for the first time, the partitioning kinetics of carbon, manganese and silicon in a medium Mn steel during the Q&P treatments using multi-phase field modelling. The redistribution of the interstitial and the substitutional elements between martensite (α') (described as acicular ferrite) and austenite (γ) phases is studied under different partitioning conditions. Investigations show that the homogenization times of carbon in the austenite strongly depends on the grain size and partitioning temperatures. Partitioning of manganese and silicon is observed to happen at much higher partitioning temperatures and times compared to carbon. Silicon is enriched on the martensite (α') side of the α'/γ interface, indicating the chances of carbide formation in the austenite region. Results from this research provides an understanding of the microstructural development during the application of Q&P heat treatments that is difficult to gain solely with the experiments.

Keywords: Phase field modelling, Quenching & Partitioning, Partitioning kinetics